

Time	Skydrol	Distilled water	5% Acid Acetic	10% Acid Lactic	Trichloroethane	Ethanol
03 Weeks	-0.12	0.30	0.90	0.65	0.05	2.35
03 months	-0.25	0.50	1.50	1.15	0.05	1.20

Pot-life:

Environment temperature	+20°C	+25°C	+30°C	+35°C
Pot-life (minutes)	60	50	30	15

Waiting time between layers

Environment temperature	+20°C	+25°C	+30°C	+35°C
Waiting time: Minimum	24 hours	20 hours	16 hours	12 hours
Maximum	36 hours	30 hours	24 hours	24 hours
Pedestrian	36 hours	30 hours	24 hours	20 hours
Light loading capacity	5 days	4 days	3 days	2 days
Completely cured	10 days	10 days	7 days	5 days

GUIDE TO APPLICATION

Coating system:	<ul style="list-style-type: none"> If the surface is concrete, mortar, natural stone, or artificial stone, apply a layer of BestPrimer EP601 or BestPrimer EP603 depending on the surface moisture before applying BestCoat EP716. If the surface is metal, at least 2 layers of BestCoat EP716 must be applied after the surface is completely cleaned using the appropriate method.
Surface preparation:	<p>Concrete surface: Compressive strength: ≥ 20 MPa, tensile strength: ≥ 1.5 MPa. The surface must be flat, solid, and dry (maximum substrate moisture content is 4%), and impurities, broken pieces, and dust should be removed.</p> <p>Metal surface: Free from rust, grease, or other impurities such as dust, water,...</p>
Mixing:	<p>Mixing under the right ratio by slowly stirring (at a speed of 300 to 400 rpm). The minimum mixing time is 03 minutes and can be longer until it reaches the required homogeneity. Rest for about 02 minutes then stir again before application.</p>
Application:	<p>Apply BestCoat EP716 with a roller, brush, or spray equipment.</p> <p>Notes: When applying the second layer, if there is time over waiting time must sandy the surface by sustainable methods.</p> <p>Do not use mixtures that are time over working time.</p>
Cleaning:	<p>Use BestThinner SC-01 to clean equipment immediately after work.</p>
Safety:	<p>Both components are not the type of dangerous, flammable product. However, component B is alkalinity which can irritate the skin during prolonged contact. In case of accidental eye contact, wash with fresh water several times before taking the pain tain to the nearest medical advice immediately.</p> <p>Disposal of leftover materials according to local regulations.</p>
Disclaimer:	<p><i>The technical information and application instructions in documents of BESTMIX are based on BESTMIX's current knowledge and practical experience. The information here only describes the general nature of the product, so users should test the product for each purpose. BESTMIX has the right to change the features of our product, user must always refer to the latest technology product.</i></p>