

BestSeal AC403

Multipurpose admixture: water-proofing, sealing, two components

Description:	BestSeal AC403 is a two-component waterproofing cement-based. It provides a special flexible, high bonding strength and durable waterproofing membrane. It also can bond with all silicate-based substrates: Brick, mortar, concrete, and gypsum.
Application:	BestSeal AC403 is used for waterproofing, sealing cracks, and repairing the surface of the basement, bathroom, kitchen area, balconies, terraces, flat roofs, and wet areas before ceramic tiling.
Advantage:	<ul style="list-style-type: none"> • Good adhesion, hardness, and optimal anti-cracks. • Quickly dry, saving waiting time and limiting risks to the environment. • Elastics, anti- peel in case of membrane movement by thermals. • Good bonding to silicate-based. • Create a seamless waterproof membrane, with no joints; • Easy to apply, and maintain, can waterproof residential water surfaces. • Non-toxic and non-polluted, friendly to the environment

SPECIFICATION

Packaging:	15 kg/ set; 30kg /set.
Shelf life:	12 months from the date of manufacturing in unopened condition.
Appearance:	Component A: Milky white liquid. Component B: Light grey, dry powder. Mixture A+B: Thickened liquid, dark grey after hardening.
Mass volume density:	Component A: 1.02 kg/ liter; Component B: 1.20 kg/liter
Density:	Component A: 1.02 ± 0.01 kg/ liter (25°C) Component B: 2.88 ± 0.02 kg/ iter (25°C) Freshly mixed mortar: 1.98 ± 0.05 kg/ liter (25°C)
Mixing ratio:	Component A: Component B = 1:2 (by weight).
Application temperature/ Ambient Air Temperature	Minimum: + 10°C Maximum : + 35°C
Chemical resistance:	Resistance with water, oil, and fuels.
Mechanical properties:	Anti tearing, abrasion, high adhesion strength, and not peeling.

BESTMIX CORPORATION

www.bestmix.vn

HEAD OFFICE:
 Lot D1, D1&N3 Rd., Nam Tan Uyen IP,
 Tan Uyen Town, Binh Duong Province,
 Tel: (027) 4365 3990 - 4365 3991
 Email: info@bestmix.com.vn

HCMC OFFICE 1:
 378-384 Cong Hoa Str., Ward 13,
 Tan Binh Dist., Ho Chi Minh City
 Tel: (028) 3810 7995 (7996, 7997)
 Email: bm1@bestmix.com.vn

HCMC OFFICE 2:
 23 Nguyen Huu Canh Str., Ward 22,
 Binh Thanh Dist., Ho Chi Minh City
 Tel: (028) 3899 0339 - 3899 0340
 Email: bm2@bestmix.com.vn

NHA TRANG OFFICE:
 989 Le Hong Phong Street,
 Phuoc Long Ward, Nha Trang City
 Tel: 090 545 3579
 Email: bm3@bestmix.com.vn

CENTRAL BRANCH:
 478B1 Dien Bien Phu Street,
 Thanh Kha District, Da Nang City
 Tel: (023) 6371 5299 - 6371 5399
 Email: bm4@bestmix.com.vn

NORTHERN BRANCH:
 TT6.2 - 65, Dai Kim Urban Area,
 Hoang Mai District, Ha Noi City
 Tel: (024) 3200 8234
 Email: bm5@bestmix.com.vn

